



# T A S M A N

## LEATHER NORTH CAROLINA

EDINBURG

### TECHNICAL SPECIFICATIONS

RAW MATERIAL:

USA STEERS/COWS

COLORS:

CHESTNUT – SANDCASTLE – LANDER – CEMENT – MARQUOIS WHEAT – CAMEL – SANDBANK – GREY –  
DESERT SKY – BARK – WOODLAND – ROYAL NAVY – BLACK CHERRY – SEQUOIA

Product	Laboratory specs				Inspection specs	
	Description	Method	Requirement	Units	Description	Requirement
E D I N B U R G	Tensile Strength	CIA 800	355 MIN	N/cm <sup>2</sup>	Thickness	1.1 +/- .01 mm
	Elongation at Break	CIA 800	>40	%	Brightness	2 - 2.5
	Slit Tear Strength	ISO 3377-2	MIN 30	N	Color	According to the master sample
	Flexing	ASTM D 2097	No cracks at 60 000 cycles	Flexing		
	Crocking Dry	AATCC8	Min 4 at 10 cycles	GS		
	Crocking Wet	AATCC8	Min 4 at 10 cycles	GS		
	Finish Adhesion (Dry)	DIN EN ISO 11644	MIN 3	N/CM		