



T A S M A N
LEATHER NORTH CAROLINA

STONEWOOD

TECHNICAL SPECIFICATIONS

RAW MATERIAL:

AMERICAN BISON

COLORS:

DEEP BLUE – VANILLA – ACORN – ASHEN – VINTAGE - COAL

Product	Laboratory specs				Inspection specs	
	Description	Method	Requirement	Units	Description	Requirement
S T O N E W O O D	Tensile Strength	CIA 800	355 MIN	N/cm ²	Thickness	1.1 +/- .01 mm
	Elongation at Break	CIA 800	>40	%	Brightness	1.5-2
	Slit Tear Strength	ISO 3377-2	MIN 30	N	Color	According to the master sample
	Flexing	ASTM D 2097	No cracks at 60 000 cycles	Flexing		
	Crocking Dry	AATCC8	Min 4 at 5 cycles	GS		
	Crocking Wet	AATCC8	Min 4 at 5 cycles	GS		
	Finish Adhesion (Dry)	DIN EN ISO 11644	MIN 3	N/CM		