



T A S M A N
LEATHER NORTH CAROLINA

ANALUX

TECHNICAL SPECIFICATIONS

RAW MATERIAL: AMERICAN BISON
 COLORS: ANTELOPE – BLACK – COGNAC – CREAM – GUNMETAL - PRAIRIE BROWN – SADDLE –
 TAUPE – TOBACCO – CHOCOLATE -BLOOD RED - DARK BROWN - FLORENTINE

| Product | Laboratory specs | | | | Inspection specs | |
|----------------------------|-----------------------|------------------|----------------------------|-------------------|------------------|--------------------------------|
| | Description | Method | Requirement | Units | Description | Requirement |
| A N A L U X | Tensile Strength | CIA 800 | 355 MIN | N/cm ² | Thickness | 1.5 +/- .01 mm |
| | Elongation at Break | CIA 800 | >40 | % | Brightness | 2 - 2.5 |
| | Slit Tear Stregth | ISO 3377-2 | MIN 30 | N | Color | According to the master sample |
| | Flexing | ASTM D 2097 | No cracks at 60 000 cycles | Flexing | | |
| | Crocking Dry | AATCC8 | Min 4 at 5 cycles | GS | | |
| | Crocking Wet | AATCC8 | Min 4 at 5 cycles | GS | | |
| | Finish Adhesion (Dry) | DIN EN ISO 11644 | MIN 3 | N/CM | | |